



WAVEOPTICS

# G.652.D

Optical Fiber Specifications

**TECHNICAL  
INFORMATION**



## WAVEOPTICS Fiber (F) G.652.D

Optical fiber specifications before cabling

CHARACTERISTICS		WAVEOPTICS G.652.D
Fiber Code		F
Attenuation	1310 nm	$\leq 0.33$ dB/km
	1550 nm	$\leq 0.19$ dB/km
Attenuation vs Wavelength Max. difference of $\alpha$	1285-1330 nm	$\leq 0.05$ dB/km
	1525-1575 nm	$\leq 0.05$ dB/km
Mode field diameter	1310 nm	$9.2 \pm 0.4$ $\mu$ m
Max. PMD per fiber		$\leq 0.15$ ps/ $\sqrt$ km
Point discontinuities	1310 nm	$\leq 0.05$ dB
	1550 nm	$\leq 0.05$ dB
Cutoff wavelength		$\leq 1260$ nm
Dispersion values	1550 nm	$\leq 18$ ps/nm*km
	1625 nm	$\leq 22$ ps/nm*km





## Physical Characteristics

CHARACTERISTICS	WAVEOPTICS G.652.D
Cladding diameter	$125.0 \pm 0.7 \text{ } \mu\text{m}$
Core-cladding concentricity error	$\leq 0.6 \text{ } \mu\text{m}$
Cladding non-circularity	$\leq 1.0 \%$
Coating diameter	$245.0 \pm 7 \text{ } \mu\text{m}$
Coating-cladding concentricity error	$\leq 12 \text{ } \mu\text{m}$

## Environmental Characteristics

CHARACTERISTICS	CONDITIONS	WAVEOPTICS G.652.D
Temperature cycling	$-60^{\circ}\text{C}$ to $+85^{\circ}\text{C}$	$\leq 0.05 \text{ dB/km}$
Water immersion	$23^{\circ}\text{C} \pm 2^{\circ}\text{C}$	$\leq 0.05 \text{ dB/km}$
High temperature aging	$85^{\circ}\text{C} \pm 2^{\circ}\text{C}$	$\leq 0.05 \text{ dB/km}$

